



DOW™ LDPE 535I

The Dow Chemical Company - Low Density Polyethylene Resin

Sunday, February 01, 2015

General Information

Product Description

- Complies with U.S. FDA 21 CFR 177.1520(c) 2.2
- Complies with Canadian HPFB No Objection (With Limitations)
- Complies with EU, No 10/2011
- Consult the regulations for complete details

General

Material Status	• Commercial: Active
Availability	• Latin America • North America
Agency Ratings	• EU No 10/2011 • FDA 21 CFR 177.1520(c) 2.2 • HPFB (Canada) No Objection ¹
Forms	• Pellets
Processing Method	• Blown Film

ASTM & ISO Properties ²

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.927		ASTM D792
Melt Mass-Flow Rate (190°C/2.16 kg)	1.9	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	2.0	mil	
Film Puncture Resistance (2.0 mil)	35.0	ft-lb/in ³	Internal Method
Film Toughness - MD (2.0 mil)	2370	ft-lb/in ³	ASTM D882
Film Toughness - TD (2.0 mil)	2510	ft-lb/in ³	ASTM D882
Tensile Strength - MD (Yield, 2.0 mil)	1970	psi	ASTM D882
Tensile Strength - TD (Yield, 2.0 mil)	1990	psi	ASTM D882
Tensile Strength - MD (Break, 2.0 mil)	3620	psi	ASTM D882
Tensile Strength - TD (Break, 2.0 mil)	3060	psi	ASTM D882
Tensile Elongation - MD (Break, 2.0 mil)	550	%	ASTM D882
Tensile Elongation - TD (Break, 2.0 mil)	770	%	ASTM D882
Dart Drop Impact (2.0 mil)	86	g	ASTM D1709A
Elmendorf Tear Strength - MD (2.0 mil)	360	g	ASTM D1922
Elmendorf Tear Strength - TD (2.0 mil)	470	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	208	°F	ASTM D1525
Melting Temperature (DSC)	237	°F	Internal Method
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 2.00 mil)	72		ASTM D2457

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	421	°F

DOW™ LDPE 535I

The Dow Chemical Company - Low Density Polyethylene Resin

Extrusion Notes

Fabrication Conditions For Blown Film:

- Screw Size: 2.5 in. (63.5 mm); 24:1 L/D
- Screw Type: Single Flight with Maddock Mixer
- Die Gap: 40 mil (1.0 mm)
- Melt Temperature: 420 °F (216 °C)
- Output: 10 lb/hr/in. of die circumference
- Die Diameter: 6 in.
- Blow-Up Ratio: 2.5:1

Notes

¹ With limitations

² Typical properties: these are not to be construed as specifications.