Crastin® HR5315HFS NC010
THERMOPLASTIC POLYESTER RESIN

Product Description
Crastin® HR5315HFS is a 15% glass fiber reinforced, moderatley toughened, hydrolysis resistant polybutylene terephthalate for injection molding.

General			
Material Status	• Preliminary Data [1]		
Availability	• Africa & Middle East • Asia Pacific • Central America	• Europe • Latin America • North America	• South America
Filler / Reinforcement	• Glass Fiber Reinforcement, 15% Filler by Weight		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		
Part Marking Code (ISO 11469)	• >PBT-IGF15<		
Resin ID (ISO 1043)	• PBT-IGF15		
Product Category	• Glass Reinforced Resins	• Hydrolysis Resistant Resins	

Physical	Nominal Value Unit	Test Method
Density	1.38 g/cm³	ISO 1183
Mechanical	**Nominal Value Unit**	**Test Method**
Tensile Modulus (23°C)	5000 MPa	ISO 527-2
Tensile Stress (Break, 23°C)	100 MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.4 %	ISO 527-2
Impact	**Nominal Value Unit**	**Test Method**
Charpy Notched Impact Strength (23°C)	11 kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	60 kJ/m²	ISO 179/1eU
Thermal	**Nominal Value Unit**	**Test Method**
Heat Deflection Temperature		ISO 75-2/A
1.8 MPa, Unannealed	200 °C	
Melting Temperature [3]	225 °C	ISO 11357-3
Flammability	**Nominal Value Unit**	**Test Method**
Flammability Classification (1.50 mm)	HB	IEC 60695-11-10, -20

Injection	Nominal Value Unit
Drying Temperature	110 to 130 °C
Drying Time	3.0 to 4.0 hr
Suggested Max Moisture	< 0.040 %
Processing (Melt) Temp	240 to 255 °C
Melt Temperature, Optimum	250 °C
Mold Temperature	30.0 to 130 °C
Mold Temperature, Optimum	80 °C

Notes

[1] The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

[2] Typical properties: these are not to be construed as specifications.

[3] 10°C/min

To find out more, visit DuPont Performance Polymers or contact the nearest DuPont location.

North America
Tel: +1 302 999-4592
Toll-Free (USA): 800 441-0575

Asia Pacific
Tel: +81 3 5521 8600

Europe/Middle East/Africa
Tel: +41 22 717 51 11

Copyright © 2013 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.

Test temperatures are 23°C unless otherwise stated.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee favorable results, makes no warranties and assumes no liability in connection with any use of this information. All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products.
CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-4 and DuPont CAUTION Regarding Medical Applications … H-50102-4

To find out more, visit DuPont Performance Polymers or contact the nearest DuPont location.

North America
Tel: +1 302 999-4592
Toll-Free (USA): 800 441-0575

Asia Pacific
Tel: +81 3 5521 8600

Europe/Middle East/Africa
Tel: +41 22 717 51 11

Copyright © 2013 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.