



# Geon™ Vinyl Dry Blend E7130

## Rigid Polyvinyl Chloride

### Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	• South America
Features	• High Impact Resistance		
Uses	• Building Materials	• Fencing & Decking	• Outdoor Applications
Forms	• Powder		
Processing Method	• Extrusion	• Profile Extrusion	

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.45	1.45 g/cm <sup>3</sup>	ASTM D792
PVC Cell Classification	1-42444-33-0101	1-42444-33-0101	ASTM D4216
PVC Cell Classification	16354	16354	ASTM D1784
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus <sup>2</sup>	430000 psi	2970 MPa	ASTM D638
Tensile Strength <sup>2</sup> (Yield)	6850 psi	47.2 MPa	ASTM D638
Flexural Modulus	422000 psi	2910 MPa	ASTM D790
Flexural Strength	12700 psi	87.4 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact - Across Flow 73°F (23°C), 0.125 in (3.18 mm), Compression Molded	23 ft-lb/in	1200 J/m	ASTM D256A
Drop Impact Resistance 73°F (23°C) <sup>3</sup>	1.60 in-lb/mil	71.2 J/cm	ASTM D4226
73°F (23°C) <sup>4</sup>	3.50 in-lb/mil	156 J/cm	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D)	82	82	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	165 °F	73.9 °C	ASTM D648
CLTE - Flow	0.000036 in/in/°F	0.000065 cm/cm/°C	ASTM D696
Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
AAMA 303	Pass	Pass	ASTM D4726

### Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	380 to 400 °F	193 to 204 °C

Copyright © 2013 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

## Notes

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> Type I, 0.20 in/min (5.1 mm/min)

<sup>3</sup> Procedure A, C.125 Dart

<sup>4</sup> Procedure B, C.125 Dart

## CONTACT INFORMATION

### Americas

Canada - St Remi de Napierville  
+1 888 588 4366

Mexico - Toluca  
+52 722 2790200

United States - Avon Lake  
+1 440 930 1000

### Asia

China - HouJie Town, Dongguan  
City,  
+86 769 8998 8158

### Europe

Belgium - Assesse  
+32 83 660 211



*Beyond Polymers.*

*Better Business Solutions.™*

[www.polyone.com](http://www.polyone.com)

### PolyOne Americas

33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000  
+1 866 POLYONE

### PolyOne Asia

No. 88 Guoshoujing Road  
Z.J Hi-tech Park, Pudong  
Shanghai, 201203, China  
+86 21 5080 1188

### PolyOne Europe

6 Giallewee  
+352 269 050 35

Copyright ©, 2013 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.